

PRODUCT SPECIFICATION

CMP 95

Parameters	Unit	Specification	
Grammage	g/m ²	91	- 99
Moisture Content	%	6.0	- 9.0
Ring Crush (CD)	N	≥	83
Ring Crush (CD), (Conversion: 1N = 0.102 kgf)	kgf	≥	8.5
Cobb Value (Top, 1 min)	g/m ²	≤	80
Cobb Value (Bottom, 1 min)	g/m ²	≤	80
Ply Bond	J/m ²	≥	250
CMT	N	≥	128

Testing condition: Temperature 23±1 °C and Relative Humidity 50±2 % for 24 hours.

Remarks: Our products are not for pharmaceutical and direct food contact purposes.