

PRODUCT SPECIFICATION

CMP 90

Parameters	Unit	Specification		
Grammage	g/m ²	86	-	94
Moisture Content	%	6.0	-	9.0
Ring Crush (CD)	N	≥	79	
Ring Crush (CD), (Conversion: 1N = 0.102 kgf)	kgf	≥	8.1	
Cobb Value (Top, 1 min)	g/m ²	≤	80	
Cobb Value (Bottom, 1 min)	g/m ²	≤	80	
Ply Bond	J/m ²	≥	250	
CMT	N	≥	115	

Testing condition: Temperature 23±1 °C and Relative Humidity 50±2 % for 24 hours.

Remarks: Our products are not for pharmaceutical and direct food contact purposes.