

PRODUCT SPECIFICATION

CMP 105

Parameters	Unit	Specification		
Grammage	g/m ²	101	-	109
Moisture Content	%	6.0	-	9.0
Ring Crush (CD)	N	≥	92	
Ring Crush (CD), (Conversion: 1N = 0.102 kgf)	kgf	≥	9.4	
Cobb Value (Top, 1 min)	g/m ²	≤	80	
Cobb Value (Bottom, 1 min)	g/m ²	≤	80	
Ply Bond	J/m ²	≥	250	
CMT	N	≥	160	

Testing condition: Temperature 23±1 °C and Relative Humidity 50±2 % for 24 hours.

Remarks: Our products are not for direct food contact purpose.